



TDS BIIR-2132

Panjing Cenway Materials Co., Ltd.

ZY-PXH-PZB006-2021-1

Composition

Copolymer rubber of brominated isobutylene-isoprene with low Mooney viscosity

Basic Properties	Unit	Standard	Test Method
Product Form		Off-white bales	Visual
Volatiles	wt%	0	GB/T 24131.2
Mooney Viscosity ML(1+8)125	MU	28-36	GB/T1232.1
Total Ash	wt%		GB/T 4498.1
Bromine Content	wt%	1.90-2.30	Q/XH-FX 100
Stabilizer			



TDS B I I R-2132

Panjing Cenway Materials Co., Ltd.

ZY-PXH-PZB006-2021-1

Storage Life & Conditions

Two years from production date, recommended to store & transport below 35 , no exposure to sunlight.

Statement

This product data sheet was developed pursuant to Panjin CENWAY sampling and test procedures. If requested, these test methods are available. Unless otherwise agreed in writing, the data are subject to change without notice. This document may not be distributed, displayed, copied or altered without Panjin
